

Maxwell Road, Stevenage
Hertfordshire
SG1 2EW, UK

T: +44(0) 1438 777 700
F: +44(0) 1438 777 800
E: info@fira.co.uk
W: www.fira.co.uk

Trimproof Ltd. t/a Chieftain Fabrics

Wellington Place

Trim

C15 W248

Ireland

Our Ref: **TFTXF59220**

Date: 28 July 2015

Delivery Date: 10 April 2015

Test Dates: 10 June – 28 July 2015

For the attention of Ms Malgorzata Kawka

SAMPLE(S) FOR TEST:

One, Artificial leather – Ref: TRIMCELL

Note: The above descriptions are as supplied by the client and have not been verified by FIRA who can take no responsibility for the accuracy of the description.

TEST REQUIREMENTS:

Tensile strength - BS EN ISO 13934-1: 2013
Tear strength - BS EN ISO 13937-3: 2000
Abrasion - BS EN ISO 12947-2: 1998
Bursting strength - BS EN ISO 13938-2:1999*
Adhesion of finish – BS EN ISO 2411:2000*

RESULT:

Severe Contract
Severe Contract
Severe Contract
Informative
Informative

* The standard has been subcontracted to another UKAS accredited laboratory

FIRA is a UKAS TESTING Laboratory No. 0174

Tests marked "Not UKAS Accredited" in this Report are not included in the UKAS Accreditation Schedule for our laboratory.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

This Report relates to the sample(s) submitted for test and no others. Additions, deletions or alterations are not permitted.

Test reports are given to the client in confidence, and may only be reproduced in whole or in part with written permission from FIRA International Limited. Note that the words "**tested by FIRA**" may be used in subsequent publicity for the product; "approved" must **not** be used.

Tests are carried out on the understanding that neither FIRA International Limited nor its officers can accept any legal responsibility for information or advice given or opinions expressed whether in response to specific enquiries or otherwise.

This Report is given subject to the Terms of Business of FIRA International Limited which are available at www.fira.co.uk/document/fira-terms-and-conditions.pdf



TECHNICAL REPORT

DESCRIPTION

Item: One, Artificial leather – Ref: TRIMCELL

Initial Inspection: Condition as new

Conditioning: In accordance with BS EN ISO 139: 2005+A1:2011; >24 hours at 20±2°C & 65±4% relative humidity; preconditioning: 4 hours at 50°C

Testing: In accordance with BS EN ISO 139: 2005+ A1:2011 20±2°C & 65±4% relative humidity

TEST RESULTS

DETERMINATION OF MAXIMUM FORCE & ELONGATION AT MAXIMUM FORCE USING THE STRIP METHOD BS EN ISO 13934-1: 2013

Sample	Breaking Strength (N)		Elongation (%)	
	Parallel to warp	Parallel to weft*	Parallel to warp	Parallel to weft*
1	464	347*	86	138*
2	485	345*	92	133*
3	465	355*	87	136*
4	513	371*	94	138*
5	370	353*	77	138*
Mean	460	354*	87	138*

* Indicative test results; due to construction of the fabric a jaw breakage was observed on all tested specimens. Test results reported are informative only.

Gauge length used: 200mm Rate of elongation: 100mm/min Slack set procedure used
State of specimen: conditioned

According to BS 2543: 2004 a minimum breaking strength of **350N** warp and weft is required for light domestic and general domestic use, and **400N** for heavy domestic, general contract or severe contract use applications. Elongation results supplied for information only; performance for upholstery fabrics is dependant on breaking strength. An uncertainty of measurement budget of +/- 1.67% is applicable for all tensile strength borderline passes/failures.

DETERMINATION OF TEAR FORCE OF WING-SHAPED TEST SPECIMENS (SINGLE TEAR METHOD) BS EN ISO 13937-3: 2000

Sample	Parallel to warp (N)	Parallel to weft (N)
1	35	44
2	33	43
3	38	43
4	35	43
5	36	41
Mean	35	43

According to BS 2543: 2004 a minimum tear strength of **15N** is required for fabrics intended for light domestic use, **20N** is required for fabrics intended for general domestic use, and **25N** is required for heavy domestic, general contract and severe contract applications. Mean values calculated electronically.

TECHNICAL REPORT

MARTINDALE ABRASION TEST – BS EN 14465: 2003 Annex A (Method BS EN ISO 12947-2: 1998)

Specimen breakdown, defined in BS EN 14465: 2003 as a hole was observed did not occur, therefore the test was stopped as the required number of cycles was completed:

Specimen A 100,000 cycles
Specimen B 100,000 cycles
Specimen C 100,000 cycles

Overall result 100,000 cycles

At 3,000 cycles the colour change assessed as in BS EN 20105-A02 was grade **4-5**.

The abrasion resistance is evaluated by the end point method with an 8-fold magnification aid. The specimens are mounted in specimen holders with foam backing and the specimen pressure used for upholstery use applications is 12kPa.

BURSTING STRENGTH – BS EN ISO 13938-2:1999

Number of samples tested: 5
Equipment used: TruBurst²
Test area: 50cm²

Mean Burst (kPA)	346.4
Mean height at burst (mm)	33.8

ADHESION OF FINISH – EN ISO 2411/BS3424/-7

Mid Pint N/50mm Longitudinal	Mid Point N/50mm Transverse
*	*

**Inseparable due to the adhesive strength being stronger than the coating*

TECHNICAL REPORT

CONCLUSION

The material properties for BS EN 14465: 2003 indicates that this fabric reaches a performance level of:

Test performed	Performance level
BS EN ISO 13934-1:2013	B
BS EN ISO 13937-3: 2000	B
BS EN 14465: 2003 Annex A (BS EN ISO 12947-2:1998)	A

According to BS 2543: 2004, this fabric is suitable in respect of tensile strength, tear strength and abrasion resistance properties for severe contract (SC) upholstery use application.

Tested and reported by: Agnieszka Haines

Approved by: Stephen Cotton
Technical Specialist

A Grading Assessment Tolerance of +/-0.5 of grade is applicable for all Colour Fastness assessments due to their subjective nature. This uncertainty was not applied to the reported results and therefore it needs to be considered when determining compliance with a specification.

***** End of Report *****