

Maxwell Road, Stevenage
Hertfordshire
SG1 2EW, UK

T: +44(0) 1438 777 700
F: +44(0) 1438 777 800
E: info@fira.co.uk
W: www.fira.co.uk

Chieftain Fabrics

Trim
Co.Meath
Ireland

Our Ref: **TFTXF70907**

Date: 21 February 2017

Delivery Date: 16 January 2017

Test Dates: 18 January - 20 February 2017

For the attention of Sinead Doyle

SAMPLE(S) FOR TEST:

One, Coated fabric – Ref: Just Colour

Note: The above descriptions are as supplied by the client and have not been verified by FIRA who can take no responsibility for the accuracy of the description.

TEST REQUIREMENTS:

Determination of abrasion – BS EN ISO 5470-2: 2003, Method 1

RESULT:

Performance Level A

This Report relates to the sample(s) submitted for test and no others. Additions, deletions or alterations are not permitted.

Test reports are given to the client in confidence, and may only be reproduced in whole or in part with written permission from FIRA International Limited. Note that the words "**tested by FIRA**" may be used in subsequent publicity for the product; "approved" must **not** be used.

Tests are carried out on the understanding that neither FIRA International Limited nor its officers can accept any legal responsibility for information or advice given or opinions expressed whether in response to specific enquiries or otherwise.

This Report is given subject to the Terms of Business of FIRA International Limited which are available at www.fira.co.uk/document/fira-terms-and-conditions.pdf

TECHNICAL REPORT

DESCRIPTION

Item: One, Coated fabric – Ref: Just Colour

Initial Inspection: Condition as new

Conditioning: In accordance with BS 3424: Part 2: 1992 ISO 2231: 1989; >16 hours at 20±2°C & 65±5% relative humidity.

Testing: In accordance with BS EN ISO 139: 2005+ A1:2011 20±2°C & 65±4% relative humidity. Please note that conditions were outside of these ranges for 45 minutes during test. We consider this negligible due to the length of the test.

TEST RESULTS

RUBBER- OR PLASTICS-COATED FABRICS – DETERMINATION OF ABRASION RESISTANCE – PART 2: MARTINDALE ABRADER BS EN ISO 5470-2: 2003, Method 1.

Specimen failure, defined in BS EN 15618: 2009 as a damage rating greater than 2 did not occur, therefore the test was stopped as the required number of cycles was completed:

Specimen A	500,000 cycles
Specimen B	500,000 cycles
Specimen C	500,000 cycles
Specimen D	500,000 cycles

Overall result 500,000 cycles

At 500,000 cycles the damage rating assessed as in BS EN ISO 5470-2: 2003 was grade 1.

The abrasion resistance is evaluated by the end point method without magnification. The specimens were mounted in specimen holders without foam backing and the specimen pressure used for upholstery use applications is 12kPa.

TECHNICAL REPORT

CONCLUSION

The material properties for BS EN 15618: 2009 indicates that this fabric reaches a performance level of:

Test performed	Performance level
BS EN ISO 5470-2: 2003	A

A Grading Assessment Tolerance of +/-0.5 of grade is applicable for all damage rating assessments due to their subjective nature. This uncertainty was not applied to the reported results and therefore it needs to be considered when determining compliance with a specification.

Tested by: Gemma Buffham
Reported by: Deme-Daisy Clarke-Phipps
Approved by: Gemma Buffham
Senior Technician

***** End of Report *****