

Our Ref: SW/LS/JM

28 March 2019

Report 340147/5

Page 1 of 3

Chieftain Fabrics
Fair Green
Trim
Co. Meath
Ireland

Contact: Dan Kinsella; Sinead Doyle

DATE RECEIVED : 21 MAR 2019
 FABRIC SUPPLIER : CHIEFTAIN FABRICS
 QUALITY/REFERENCE : RAVEL
 REPUTED FIBRE CONTENT : 100% POLYESTER
 FABRIC DESCRIPTION : WOVEN
 COLOUR/DESIGN : WOVEN
 END USE : UPHOLSTERY
 ORDER NUMBER : SINEAD

PERFORMANCE STANDARD : BS 2543:2004 & BS EN 14465:2003 + A1:2006



REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Hydrostatic head	BS EN 20811:1992 (1996)			No requirement
Hydrostatic head	BS EN 20811:1992 (1996)			No requirement



S. WISEMAN
LABORATORY DIRECTOR



L. SHERIDAN
LABORATORY MANAGER



28 March 2019

Report 340147/5

Page 2 of 3

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

PHYSICAL

BS EN 20811:1992 (1996) Hydrostatic Head

Yellow

Sample area	100cm ²
Test atmosphere	20°C 65% R.H
Water temperature	20°C
Rate of rise of water pressure	60cm/1min

Test 1	23 cms/H ₂ O
Test 2	25 cms/H ₂ O
Test 3	26 cms/H ₂ O
Test 4	23 cms/H ₂ O
Test 5	25 cms/H ₂ O
Mean	24.4 cms/H ₂ O

Requirement:

BS EN 20811:1992 (1996) Hydrostatic Head

Green

Sample area	100cm ²
Test atmosphere	20°C 65% R.H
Water temperature	20°C
Rate of rise of water pressure	60cm/1min

Test 1	23 cms/H ₂ O
Test 2	26 cms/H ₂ O
Test 3	27 cms/H ₂ O
Test 4	23 cms/H ₂ O
Test 5	28 cms/H ₂ O
Mean	25.4 cms/H ₂ O

Requirement:

