

Our Ref: SW/LS/JM

23 April 2019

Report 341764

Page 1 of 2

Chieftain Fabrics
Fair Green
Trim
Co. Meath
Ireland

Contact: Dan Kinsella; Sinead Doyle

DATE RECEIVED : 16 APR 2019
 FABRIC SUPPLIER : CHIEFTAIN FABRICS
 QUALITY/REFERENCE : PASHA
 REPUTED FIBRE CONTENT : NOT GIVEN
 FABRIC DESCRIPTION : FAUX LEATHER
 COLOUR/DESIGN : BROWN
 END USE : UPHOLSTERY

PERFORMANCE STANDARD : BS2543:2004 & BSEN 14465:2003 + A1:2006

REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Tensile strength	BS EN ISO 1421:2016			No requirement
Tear strength	BS EN 13937-3:2000			No requirement
Tear strength	BS EN ISO 4674-1:2003 METHOD A			No requirement
Tear strength	BS EN ISO 4674-1:2016 METHOD B			No requirement




S. WISEMAN
LABORATORY DIRECTOR

L. SHERIDAN
LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



Report 341764

PHYSICAL

BS EN ISO 1421:2016 Method 1

	Length	Width	Requirement:
Mean	429.5 N	222.7 N	No requirement

BS EN 13937-3:2000 Wing Tear Strength

	Length	Width	Requirement:
Mean	10.2 N	18.6 N	No requirement

BS EN ISO 4674-1:2003 METHOD A

	Length	Width	Requirement:
Mean	19.1 N	35.1 N	No requirement

BS EN ISO 4674-1:2016 METHOD B

	Length	Width	Requirement:
Mean	10.3 N	17.6 N	No requirement
