

Our Ref: SW/LS/RM

12 August 2019

Report 347427


Page 1 of 3

Chieftain Fabrics
Fair Green
Trim
Co. Meath
Ireland

Contact: Sinead Doyle

DATE RECEIVED : 19 JUL 2019
 QUALITY/REFERENCE : JUST COLOUR
 REPUTED FIBRE CONTENT : 100% PVC
 FABRIC DESCRIPTION : COATED
 COLOUR/DESIGN : BLACK
 END USE : UPHOLSTERY
 ORDER NUMBER : SINEAD

PERFORMANCE STANDARD : BS 2543:2004 & BS EN 14465:2003 + A1:2006



REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Abrasion of upholstery	Abrasion Resistance BS EN ISO 12947-2: 1998 / BS EN 14465: 2003 Annex A	Pass		Level A suitable for Any End Use




S. WISEMAN
LABORATORY DIRECTOR

L. SHERIDAN
LABORATORY MANAGER



118 Lupton Avenue Leeds LS9 6ED
 Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
 Registered No. 2899980 VAT No. 613 4310 86

12 August 2019

Report 347427

Page 2 of 3

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

PHYSICAL

Abrasion Resistance BS EN ISO 12947-2: 1998 / BS EN 14465: 2003 Annex A

12 kPa load.

Number of rubs to breakdown:
Head 1 1,000000+
Head 2 1,000000+
Head 3 1,000000+
Head 4 1,000000+

Requirement:

Level A suitable for Any

End Use
