

Our Ref: SW/LS/RM

7 October 2019

Report 351606

Page 1 of 3

Chieftain Fabrics
Fair Green
Trim
Co. Meath
Ireland

Contact: Sinead Doyle

DATE RECEIVED : 2 OCT 2019
 FABRIC SUPPLIER : CHIEFTAIN FABRICS
 QUALITY/REFERENCE : TRIMCELL
 REPUTED FIBRE CONTENT : 100% PVC
 FABRIC DESCRIPTION : WOVEN
 COLOUR/DESIGN : BLACK
 END USE : UPHOLSTERY
 ORDER NUMBER : SINEAD

PERFORMANCE STANDARD : GENERAL



REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Hydrostatic head	BS 3424 Part 26 Method 29C			No requirement



S. WISEMAN
LABORATORY DIRECTOR



L. SHERIDAN
LABORATORY MANAGER



118 Lupton Avenue Leeds LS9 6ED
 Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
 Registered No. 2899980 VAT No. 613 4310 86

7 October 2019

Report 351606

Page 2 of 3

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

7 October 2019

Report 351606

Page 3 of 3

PHYSICAL

BS 3424 Part 26 Method 29C

Sample area	100cm ²
Test atmosphere	20°C 65% R.H
Water temperature	20°C
Rate of rise of water pressure	60cm/1min

Test 1	>200 cms/H ₂ O
Test 2	>200 cms/H ₂ O
Test 3	>200 cms/H ₂ O
Test 4	>200 cms/H ₂ O
Test 5	>200 cms/H ₂ O
Mean	>200 cms/H ₂ O

Requirement:



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86