

Our Ref: SW/PN/RM

29 January 2020

Report 357974

Page 1 of 2

Chieftain Fabrics
Fair Green
Trim
Co. Meath
Ireland

Contact: Sinead Doyle

DATE RECEIVED	:	23 JANUARY 2020
FABRIC SUPPLIER	:	CHIEFTAIN FABRICS
QUALITY REFERENCE	:	JUST PATTERNS
REPUTED FIBRE CONTENT	:	NOT GIVEN
FABRIC DESCRIPTION	:	WOVEN
COLOUR/DESIGN	:	HELIX SCARLETT
END USE	:	UPHOLSTERY
ORDER NUMBER	:	SINEAD

REQUEST: BS 5852:2006 "Methods of Test for the Assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources" using ignition source 5 (wood crib)

COMMENTS: The sample met the performance requirements of BS 5852:2006 Ignition Source 5.



S. WISEMAN
LABORATORY DIRECTOR



P. NEESAM
HEAD OF FLAMMABILITY

This report shall not be reproduced except in full without written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



Our Ref: SW/PN/RM

29 January 2020

Report 357974

Page 2 of 2

FIRE TESTS ACCORDING TO BS 5852:2006. Methods of Test for the Assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources.

Conditioning

Prior to testing in the ‘as received’ condition, the sample was placed in indoor ambient conditions for 72 hours and then conditioned for 24 hours in an atmosphere having a temperature of 23 ±2°C and a relative humidity of 50 ± 5%.

Procedure

Specimens of Fabric, Ref: JUST PATTERNS were mounted over combustion modified high resilience foam with a density of approximately 36kg/m³. Tests were made using ignition source 5. Pass classifications were assigned if the performance requirements stated below were met.

Requirements

<u>Ignition Source No.</u>	<u>Maximum duration allowed for progressive smouldering</u>	<u>Maximum duration allowed for flaming</u>
5	60 min after ignition of wood crib	10 min after ignition of wood crib

The following test results relate only to the ignitability of the combination of upholstery composites (BS5852: 2006, Clause 11) under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

They also only relate to the materials tested. They do not guarantee to represent the performance of production materials.

	<u>Test 1</u>	<u>Test 2</u>
Time of flame extinction (min/secs)	3.52	3.48
Progressive smouldering	No	No
Damage through full thickness	No	No
Result designation	NI (Non-ignition)	NI (Non-ignition)

Comments

The sample met the performance requirements of BS 5852:2006 Ignition Source 5.