

Our Ref: SW/BR

23 February 2021

Report 371063


Page 1 of 3

Chieftain Fabrics
Fair Green
Trim
Co. Meath
Ireland

Contact: Emily Anderson

DATE RECEIVED : 1 FEB 2021
 FABRIC SUPPLIER : CHIEFTAIN FABRICS
 QUALITY/REFERENCE : JUST PATTERNS
 REPUTED FIBRE CONTENT : PVC
 FABRIC DESCRIPTION : COATED
 COLOUR/DESIGN : HELIX GREY
 END USE : UPHOLSTERY
 ORDER NUMBER : EMILY

PERFORMANCE STANDARD : GENERAL



REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Resistance to Abrasion	BS EN ISO 5470-2:2003 Martindale Abrasion	Pass		500,000 Rubs



S. WISEMAN
LABORATORY DIRECTOR

118 Lupton Avenue Leeds LS9 6ED
 Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
 Registered No. 2899980 VAT No. 613 4310 86

23 February 2021

Report 371063

Page 2 of 3

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.

23 February 2021

Report 371063

Page 3 of 3

PHYSICAL

BS EN ISO 5470-2:2003 Martindale Abrasion *

12 kPa load.

Requirement:

500,000 Rubs

Number of rubs to breakdown:
Head 1 500,000+
Head 2 500,000+
Head 3 500,000+
Head 4 500,000+

*Tests indicated * are non-UKAS accredited.*