

Maxwell Road
Stevenage
Hertfordshire
SG1 2EW

T: +44(0) 1438 777 700
info@fira.co.uk

www.fira.co.uk

CHIEFTAIN FABRICS

Trim
Co Meath
Republic of Ireland

Our Ref: **TX-10303-S1**
Date: 08 March 2021
Delivery Date: 05 March 2021
Test Dates: 25 February - 05 March 2021

For the attention of Emily Anderson

SAMPLE(S) FOR TEST:

One, Fabric – Ref: Carino

Note: The above descriptions are as supplied by the client and have not been verified by FIRA International who can take no responsibility for the accuracy of the description.

TEST REQUIREMENTS:

Bursting Strength, BS ISO 13938-2: 2019*

*Contracted out to another UKAS accredited test laboratory

This Report relates to the sample(s) submitted for test and no others. Additions, deletions or alterations are not permitted.

Test reports are given to the client in confidence, and may only be reproduced in whole or in part with written permission from FIRA International Limited. Note that the words "**tested by FIRA International**" may be used in subsequent publicity for the product; "approved" must **not** be used.

Tests are carried out on the understanding that neither FIRA International Limited nor its officers can accept any legal responsibility for information or advice given or opinions expressed whether in response to specific enquiries or otherwise.

This Report is given subject to the Terms of Business of FIRA International Limited which are available at www.fira.co.uk/document/fira-terms-and-conditions.pdf

TECHNICAL REPORT

DESCRIPTION

One, Fabric – Ref: Carino

Initial Inspection: Condition as new

Unless otherwise stated:

Conditioning: In accordance with BS EN ISO 139: 2005+A1:2011; >24 hours at 20±2°C & 65±4% relative humidity;

Testing: In accordance with BS EN ISO 139: 2005+ A1:2011 20±2°C & 65±4% relative humidity

TEST RESULTS

BS ISO 13938-2: 2019 - Textiles. Bursting properties of fabrics. Pneumatic method for determination of bursting strength and bursting distension.

Type of Burst Obtained	Breaking Strength (kPa)
Mean	239.0

Approximate test area used: 50cm² State of specimen: conditioned

Tested by: UKAS Accredited Laboratory

Reported by: Luis Mitchell

Approved by: Stephen Cotton
Technical Specialist



***** End of Report *****

Maxwell Road
Stevenage
Hertfordshire
SG1 2EW

T: +44(0) 1438 777 700
info@fira.co.uk

www.fira.co.uk

Chieftain Fabrics

Trim

Co Meath

Republic of Ireland

Our Ref: **TX-10270-S1**

Date: 11 March 2021

Delivery Date: 18 February 2021

Test Dates: 11 March 2021

For the attention of Emily Anderson

SAMPLE(S) FOR TEST:

One, Fabric – Ref: Carino

Note: The above descriptions are as supplied by the client and have not been verified by FIRA International who can take no responsibility for the accuracy of the description.

TEST REQUIREMENTS:

Seam slippage - BS EN ISO 13936-2: 2004

RESULT:

Severe Contract

FIRA International is a UKAS TESTING Laboratory No. 0174

Tests marked "Not UKAS Accredited" in this Report are not included in the UKAS Accreditation Schedule for our laboratory.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

This Report relates to the sample(s) submitted for test and no others. Additions, deletions or alterations are not permitted.

Test reports are given to the client in confidence, and may only be reproduced in whole or in part with written permission from FIRA International Limited. Note that the words "**tested by FIRA International**" may be used in subsequent publicity for the product; "approved" must **not** be used.

Tests are carried out on the understanding that neither FIRA International Limited nor its officers can accept any legal responsibility for information or advice given or opinions expressed whether in response to specific enquiries or otherwise.

This Report is given subject to the Terms of Business of FIRA International Limited which are available at www.fira.co.uk/document/fira-terms-and-conditions.pdf



TECHNICAL REPORT

DESCRIPTION

One, Fabric – Ref: Carino

Initial Inspection: Condition as new

Unless otherwise stated:

Conditioning: In accordance with BS EN ISO 139: 2005+A1:2011; >24 hours at 20±2°C & 65±4% relative humidity;

Testing: In accordance with BS EN ISO 139: 2005+ A1:2011 20±2°C & 65±4% relative humidity

TEST RESULTS

DETERMINATION OF SLIPPAGE RESISTANCE OF YARNS AT A SEAM IN WOVEN FABRICS: FIXED LOAD METHOD - BS EN ISO 13936-2: 2004*.

	Parallel to the warp (mm)	Parallel to the weft (mm)
Seam gape at 5N	2.5	2.3

Maximum load applied: 180N

According to BS 2543: 2004 a maximum seam gape at 5N of **4mm** is specified for heavy domestic, general contract and severe contract fabrics, **6mm** for general domestic and **8mm** for light domestic fabrics intended for upholstery use applications.

*The test was carried out using 80DTex polyester cone thread which deviates from the specification stated in BS EN ISO 13936-2: 2004. Although this thread does not fully meet the specification laid down in the standard this is regarded as having no significant effect on the test.

CONCLUSION

The material properties for BS EN 14465: 2003 indicates that this fabric reaches a performance level of:

Test performed	Performance level
Seam slippage - BS EN ISO 13936-2: 2004	A

According to BS 2543: 2004, this fabric is suitable in respect of seam slippage properties for Severe Contract (SC) upholstery use applications.

A Grading Assessment Tolerance of +/-0.5 of grade is applicable for all Colour Fastness assessments due to their subjective nature. This uncertainty was not applied to the reported results and therefore it needs to be considered when determining compliance with a specification. The temperature and humidity are at the tolerances stated in the standard. Uncertainty of Measurement calculations have not been applied. FIRA Uncertainty of Measurement values are available on request.

Tested by: Nathaly Da Silva

Reported by: Luis Mitchell

Approved by: Nathaly Da Silva
Senior Technician



***** End of Report *****



Maxwell Road
Stevenage
Hertfordshire
SG1 2EW

T: +44(0) 1438 777 700
info@fira.co.uk

www.fira.co.uk

Chieftain Fabrics

Trim
Co Meath
Republic of Ireland

Our Ref: **TX-10253-S4**

Date: 10 March 2021

Delivery Date: 18 February 2021

Test Dates: 09 March 2021

For the attention of Emily Anderson

SAMPLE(S) FOR TEST:

One, Fabric – Ref: Carino

Note: The above descriptions are as supplied by the client and have not been verified by FIRA International who can take no responsibility for the accuracy of the description.

TEST REQUIREMENTS:

Tensile strength - BS EN ISO 13934-1: 2013

RESULT:

Severe Contract

FIRA International is a UKAS TESTING Laboratory No. 0174

Tests marked "Not UKAS Accredited" in this Report are not included in the UKAS Accreditation Schedule for our laboratory.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

This Report relates to the sample(s) submitted for test and no others. Additions, deletions or alterations are not permitted.

Test reports are given to the client in confidence, and may only be reproduced in whole or in part with written permission from FIRA International Limited. Note that the words "**tested by FIRA International**" may be used in subsequent publicity for the product; "approved" must **not** be used.

Tests are carried out on the understanding that neither FIRA International Limited nor its officers can accept any legal responsibility for information or advice given or opinions expressed whether in response to specific enquiries or otherwise.

This Report is given subject to the Terms of Business of FIRA International Limited which are available at www.fira.co.uk/document/fira-terms-and-conditions.pdf



TECHNICAL REPORT

DESCRIPTION

One, Fabric – Ref: Carino

Initial Inspection: Condition as new

Unless otherwise stated:

Conditioning: In accordance with BS EN ISO 139: 2005+A1:2011; >24 hours at 20±2°C & 65±4% relative humidity;

Testing: In accordance with BS EN ISO 139: 2005+ A1:2011 20±2°C & 65±4% relative humidity

TEST RESULTS

DETERMINATION OF MAXIMUM FORCE & ELONGATION AT MAXIMUM FORCE USING THE STRIP METHOD BS EN ISO 13934-1: 2013.

Sample	Breaking Strength (N)		Elongation (%)	
	Parallel to warp	Parallel to weft	Parallel to warp	Parallel to weft
1	460.0	296.9	28.9	177.8
2	445.2	292.6	28.4	172.4
3	467.5	312.2	28.5	170.5
4	439.1	298.3	29.8	173.8
5	436.6	290.1	29.3	179.6
Mean	449.7	298.0	29.0	174.8

Gauge length used: 200mm Rate of elongation: 100mm/min Slack set procedure used
State of specimen: conditioned

According to BS 2543: 2004 a minimum breaking strength of **350N** warp and weft is required for light domestic and general domestic use, and **400N** for heavy domestic, general contract or severe contract use applications.
Elongation results supplied for information only; performance for upholstery fabrics is dependant on breaking strength. An uncertainty of measurement budget of +/- 1.67% is applicable for all tensile strength borderline passes/ failures.

CONCLUSION

The material properties for BS EN 14465: 2003 indicates that this fabric reaches a performance level of:

Test performed	Performance level
Tensile strength - BS EN ISO 13934-1: 2013	B

According to BS 2543: 2004, this fabric is suitable in respect of tensile strength properties for Severe Contract (SC) upholstery use applications.

A Grading Assessment Tolerance of +/-0.5 of grade is applicable for all Colour Fastness assessments due to their subjective nature. This uncertainty was not applied to the reported results and therefore it needs to be considered when determining compliance with a specification. The temperature and humidity are at the tolerances stated in the standard. Uncertainty of Measurement calculations have not been applied. FIRA Uncertainty of Measurement values are available on request.

Tested by: Nathaly Da Silva

Reported by: Luis Mitchell

Approved by: Stephen Cotton
Technical Specialist

***** End of Report *****

